Canadian Natural Resources Limited GENERAL PRESSURE VESSEL INFORMATION Job # 10.111452									
District: Grande Prairie AB				Skid No.					
Facility: Spring Lake Gas Gathering				Location (LSD): 03-17-76-11W6M					
Vessel Name Equipment Number: Line Heater									
Orientation: Horizontal									
Status: In Service Regulatory Inspection PRESSURE VESSEL NAMEPLATE DATA									
"A" or "G" o	CRN Number:								
` , , <u> </u>				11.0409.2					
A0573076 Vessel serial number: REG-02-03				U 0408.2 Size: 36 in. X 10 ft.					
Shell thickness: 9.5 mm				Shell material: SA 36					
Head thickness: 9.5 mm				Head material: SA 36					
Tube wall thickness:				Tube material: SA 106-B					
Tube diameter:				Tube length:					
				Channel material:					
Channel thickness: 1 st Pass: 3125 PSI				Chamier material.					
Design pressure				Operating pressure		Shell:			
	2 nd Pass: 1622 PSI					Tubes:			
Design Temp.	1 st Pass: 200 Deg F.			Operating temperature		Shell: 0 – 250 Deg F.			
	2 nd Pass: 200 Deg F.					Shell. 0 – 230 Deg 1.			
						Tubes:			
X-ray: RT 1				Heat treatment: HT					
Code parameters: ASME B31.3				Coated: no					
Manufacturer: Propipe Manufacturing				Year built: 2007					
Corrosion allowance				Manway: no					
PRESSURE SAFETY VALVE NAMEPLATE DATA									
PSV Tag #	Manufacture	Model #	Serial #		Set Pro	Set Pressure Capacity		Service	
					(kPa)		(scfm)	Date	
CRN#	Service By	Block Valve		Location		7e	Code Stamp		
CIU	Service By	Block valve	Location		Size		Code Stamp		
	SERV	VICE CONDITIONS	S-INDI	ICATE ALL THA	AT APPL	Y			
Sweet	Sour X		Oil	Dil		Gas X		Water X	
Amine	LPG Co			Condensate XX		Air		Glycol X	
Other (Describe):									
Inspection IntervalPSV Service Interval									
(Determined by MIC in conjunction with Chief Inspector following guidelines of CNRL Owner-User Inspection Program)									
Donord ' '									
Reports reviewed and accepted by: Mechanical Integrity Coordinator									

Insulation Verify sealed around manways, nozzles, no damage present, and there is no egress of moisture. External Condition Assess paint condition, areas peeling, record any corrosion, damage, X Paint in good overall condition – No exposed metal.	
nozzles, no damage present, and there is no egress of moisture. External Condition Assess paint condition, areas peeling, record any corrosion, damage, areas peeling. Y and skid building. Paint in good overall condition – No exposed metal.	
egress of moisture. External Condition Assess paint condition, areas peeling, record any corrosion, damage, v Paint in good overall condition – No exposed metal.	orn sections- Sealed around saddles, nozzles
External Condition Assess paint condition, areas peeling, record any corrosion, damage, v Paint in good overall condition – No exposed metal.	lding.
areas peeling, record any corrosion, damage, Paint in good overall condition – No exposed metal.	
	d overall condition – No exposed metal.
etc (record location, size and depth of	
corrosion or damage)	
Leakage Record any leakage at flanges, X No leaks observed.	erved.
threaded joints, weep holes on repads, etc.	
Saddle/Skirt Assess condition of paint, fire Saddles: Welded directly to skid floor.	
protection, concrete. Look for corrosion, No buckling or dents.	
buckling, dents, etc. Look at vessel surface No corrosion at attachment welds to vessel.	
area near supports. Verify no signs of leakage at attachment to vessel and attachment welds	e attached to skid.
are acceptable. Ground wire attached?	
Anchor Bolts Hammer tap to ensure secure. Saddles welded to skid frame - No deformation.	led to skid frome - No deformation
Look for cracking in treads or signs of X	ieu to skiu Italiie - 140 delof mation.
deformation.	
Concrete foundation Check for cracks	
spalling, etc.	
Ladder / Platform Describe general	
condition, ensure support is secure to vessel,	
describe any hazards.	
Nozzle Assess paint, look for leakage, and Flanged and threaded nozzle are fully engaged.	threaded nozzle are fully engaged.
oncurs ctud threads are fully angued Pocord No demogra or deflections no looks	
any damage, deflection, etc. Are nozzles X Nozzles are not gusseted.	
gusseted?	
Gauges Ensure gauges are visible, working, Within operational range for service – temperature gauges	ational range for service – temperature gauge 0
no leakage, and suitable for range of MAWP/ X -250 Deg F.	
Temp.	
External Piping Ensure pipe is well Piping is well supported; no deflection, all clamps and	ll supported; no deflection, all clamps and
supported. All clamps, supports, shoes, etc. in supports are in place.	
place. Look for evidence of structural X Paint in good condition – no exposed metal.	d condition – no exposed metal.
overload, deflection, etc. Paint condition,	
external corrosion?	
Valve: Ensure no leaks are visible. Valves are	
properly supported and chained if necessary. Valves are supported properly – no leaks.	apported properly – no leaks.
PSV Ensure PSV is set at pressure at or below No PSV.	
that of vessel.	
NDE methods Was UT/ MPI done on vessel Ultrasonic corrosion survey carried out – pipe metal	
(MI coordinator to review results) thickness detected below nominal minus corrosion	
X allowance. Thickness calculations carried out:	
UT point 145 (3" Elbow) – nominal thickness is 7.6mm min thickness is 6.5mm / T min thickness is 3.5mm.	
Other min thickness is 6.5mm / 1 min thickness is 3.5mm.	is is 0.5mm / 1 mm unickness is 3.5mm.

Recommendations or corrective actions: Vessel is Fit for Service or describe corrective actions required)

(MIC to review corrective actions with Operations, discuss with Chief Inspector where necessary, and get remedial action implemented)

Recommendations: No recommendations.

Summary: Vessel is in overall good condition, visual external inspection and ultrasonic corrosion survey performed – pipe metal thickness detected below nominal minus corrosion allowance. Thickness calculations carried out to ensure sufficient metal exists for safe operation.

Date: February 27, 2012

Vessel is fit for service.

